

COLLECTION : TURDA

ARTICLE : 8263

BASIC INFORMATION

Brand	Bru	Number of colour ways	27
Tariff item number	5407920000	MID	INDDEHOM16
Country of origin	India	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	20
Full roll diameter inch	7.9	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



STANDARD
100
0611045
Centexbel

FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	Yes
NFPA 260	Yes		

COLLECTION : TURDA

ARTICLE : 8263

FABRIC SPECIFICATIONS

Composition	87% Polyester, 13% Viscose	Average yarn number	35.44
Construction	66x18	Woven	Yes
Useable width cm	1.41	Useable width inch	55.51
Full width cm	143	Full width inch	56.3
Weight g/m ²	237	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	75% filament + 25% staple
Textured or non textured	96% not textured + 4% textured		

Treatment

No treatment Yes

Type of finish

Stenter Yes

Type of print or dye

Disperse Yes Reactive Yes

Weaving type

Dobby Yes

FABRIC TYPE

There are no technical details for this section.

COLLECTION : TURDA

ARTICLE : 8263

MECHANICAL PERFORMANCE

Martindale rubs	6,000	Colour fastness to light	6
Wyzenbeek double rubs	20,000	Pilling	4
Wyzenbeek cotton duck double rubs	20,000	Wyzenbeek cotton duck type general upholstery	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	6		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	280	Tearing strength weft N	250
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	1600	Tensile strength weft N/5cm	700
Elongation - ISO 13934-1			
Elongation warp %	42.5	Elongation weft %	21
Seam slippage - ISO 13936-2			
Seam slippage warp mm	8	Seam slippage weft mm	invalid
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.05	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	-0.07	Dimensional change weft after ironing without steam	0.00

COLLECTION : TURDA

ARTICLE : 8263

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.37	Dimensional change warp after ironing	-0.27
Dimensional change weft	-0.30	Dimensional change weft after ironing	-0.13
Colour fastness ISO 105 C06	5		

Resistance to domestic washing 60° C, indicated in % - ISO 6330

Dimensional change warp	-0.80	Dimensional change warp after ironing	-0.73
Dimensional change weft	-0.57	Dimensional change weft after ironing	-0.47
Colour fastness ISO 105 C06	5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.13	Dimensional change warp after ironing	-0.07
Dimensional change weft	-0.23	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 D01	5		

COLLECTION : TURDA

ARTICLE : 8263

CONSTRUCTION

Yarn 1

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	150 den
Warp Threads per cm	33	Warp TPM	NA

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Sizes	150 den
Warp Threads per cm	33	Warp TPM	NA

Yarn 3

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Sizes	450 den
Weft Threads per cm	6	Weft TPM	NA

Yarn 4

Weft Composition	60% Viscose, 40% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Sizes	350 den	Weft Threads per cm	9
Weft TPM	NA		

Yarn 5

Weft Composition	60% Polyester, 40% Viscose	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Staple	Yes
Weft Is Textured	Yes	Weft Sizes	6 nm
Weft Textured	Yes	Weft Threads per cm	3
Weft TPM	NA		

DOWNLOADS / CERTIFICATES

There are no technical details for this section.