

COLLECTION : CROCO VELVET

ARTICLE : 8332

### BASIC INFORMATION

Brand	VPF	Number of colour ways	9
Tariff item number	6001920000	MID	CNZHETONTO
Country of origin	China	Characteristics	Velvet
Vertical repeat cm	29.60	Vertical repeat inch	11.65
Horizontal repeat cm	23.00	Horizontal repeat inch	9.06
Face in	Yes	Full roll diameter cm	28
Full roll diameter inch	11	Average piece length m	40
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

### CARE AND USAGE

Type of finish knitted

#### Care codes



Care code for bleaching Do not bleach

#### Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

### ENVIRONMENTAL STANDARDS



### FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	Yes
FMVSS 302 Pass	No	NFPA 260	Yes
NFPA 701	No		

COLLECTION : CROCO VELVET

ARTICLE : 8332

**FABRIC SPECIFICATIONS**

Composition	100% Polyester	Average yarn number	15.27
Construction	30x30	Useable width cm	1.43
Useable width inch	56.3	Full width cm	145
Full width inch	57.09	Weight g/m <sup>2</sup>	393
Thickness mm	0.000	Colouring type	Piece dyed
Filament or staple	70% Filament, 30% Staple	Textured or non textured	100% Textured
Finish type	knitted		

**Treatment**


---

No treatment	Yes
--------------	-----

**Type of print or dye**


---

Disperse	Yes
----------	-----

**FABRIC TYPE**

There are no technical details for this section.

COLLECTION : CROCO VELVET

ARTICLE : 8332

**MECHANICAL PERFORMANCE**

Martindale rubs	60,000	Colour fastness to light	5
Wyzenbeek double rubs	135,000	Pilling	4-5
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	135,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes

**Colour fastness to light - ISO 105-B02**

Colour fastness to light	5
--------------------------	---

**Colour fastness to water - ISO 105-E01**

Colour fastness to water	5
--------------------------	---

**Colour fastness to dry rub - ISO 105-X12**

Colour fastness dry rub	4-5
-------------------------	-----

**Colour fastness to wet rub - ISO 105-X12**

Colour fastness wet rub	4-5
-------------------------	-----

**Colour fastness to wear - ISO 12947-2**

Colour fastness to wear	3-4
-------------------------	-----

**Tearing strength - ISO 13937-3**

Tearing strength warp N	84	Tearing strength weft N	83
-------------------------	----	-------------------------	----

**Tensile strength - ISO 13934-1**

Tensile strength warp N/5cm	590	Tensile strength weft N/5cm	230
-----------------------------	-----	-----------------------------	-----

**Elongation - ISO 13934-1**

Elongation warp %	51	Elongation weft %	84
-------------------	----	-------------------	----

**Seam slippage - ISO 13936-2**

Seam slippage warp mm	2.0	Seam slippage weft mm	2.0
-----------------------	-----	-----------------------	-----

**Dimensional stability (indicated in %) - ISO 3759**

Dimensional change warp	0.07	Dimensional change warp after ironing with steam	-0.40
Dimensional change warp after ironing without steam	0.13	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.60	Dimensional change weft after ironing without steam	0.13

COLLECTIOON : CROCO VELVET

ARTICLE : 8332

## WASHABILITY

### Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-1.03	Dimensional change warp after ironing	-1.13
Dimensional change weft	0.17	Dimensional change weft after ironing	0.46
Colour fastness ISO 105 C06	5		

### Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.41	Dimensional change warp after ironing	-3.51
Dimensional change weft	-0.33	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 C06	5		

### Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-3.18	Dimensional change warp after ironing	0.07
Dimensional change weft	-0.23	Dimensional change weft after ironing	0.07
Colour fastness ISO 105 D01	5		

## CONSTRUCTION

### Yarn 1

Warp Composition	100% Polyester	Warp Is Not High Tenacity	Yes
Warp Is Textured	Yes	Warp Sizes	20
Warp Textured	Yes	Warp Threads per cm	30
Warp TPM	15		

### Yarn 2

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Textured	Yes	Weft Sizes	20
Weft Textured	Yes	Weft Threads per cm	30
Weft TPM	15		

## DOWNLOADS / CERTIFICATES

There are no technical details for this section.