


Chalk 8423

GENERAL INFORMATION

Composition	100% PES
Weight g/m ²	320g
Weight g/Lm	455g
Width	142cm
Min. usable Width	138cm
Piece Length	50m
Tariff code	60019200

CLEANING INSTRUCTIONS



TECHNICAL DATE

• SHRINKAGE	40° WARP	0.5%		
	WEFT	0.5%		
	60° WARP	1.25%		
	WEFT	1%		
• MARTINDALE ABRASION ISO12947-2 1998	END POINT	>45000		
	CHANGE IN COLOR	4/5 (6000 cycles)		
• SEAM SLIPPAGE EN ISO 13936-2	WARP	3mm		
	WEFT	2.33mm		
• TEAR STRENGTH EN ISO 13937-3:2000	WARP	67.61N		
	WEFT	106.01N		
• TENSILE STRENGTH ISO 13934-1	WARP	693.62N	elongation	17.38%
	WEFT	589.14N	elongation	19.39%
• COLOUR FASTNESS EN ISO 105-X12	WARP DRY WARP	4/5		
	WET WEFT DRY	4		
	WEFT WET	4/5		
		4		
• COLOUR FASTNESS TO LIGHT EN ISO 105-B02	GRADE	Col 100: 3/4		
	GRADE	Col 101: 3/4		
	GRADE	Col 102: 3/4		
	GRADE	Col 103: 3/4		
	GRADE	Col 104: 3/4		
	GRADE	Col 200: 3/4		
	GRADE	Col 300: 4		
	GRADE	Col 301: 4		
	GRADE	Col 400: 3		
	GRADE	Col 500: 3/4		
	GRADE	Col 501: 3/4		
	GRADE	Col 502: 3/4		
	GRADE	col 503: 4/5		
	GRADE	Col 600: 3/4		
	GRADE	Col 601: 3/4		
	GRADE	Col 602: 3		

Chalk 8423

GRADE	Col 603: 3/4
GRADE	Col 700: 3/4
GRADE	Col 701: 3
GRADE	Col 702: 3
GRADE	Col 800: 3/4
GRADE	Col 801: 3/4
GRADE	Col 802: 3/4
GRADE	Col 803: 3/4
GRADE	Col 804: 3/4
GRADE	Col 900: 4
GRADE	Col 901: 3/4
GRADE	Col 902: 3/4

- **PILLING ON MARTINDALE** ISO 12945-2:2000

500 RUBS	5
1000 RUBS	5
2000 RUBS	5
5000 RUBS	4/5
- **PILLING TEST** BS5811-1986

GRADE	4/5
--------------	-----