

COLLECTION : CARRARA

ARTICLE : 8437

BASIC INFORMATION

Brand	VPF	Number of colour ways	4
Tariff item number	5801370000	MID	INDDEHOM16
Country of origin	India	Characteristics	Velvet
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	25
Full roll diameter inch	9.84	Average piece length m	30
Minimum for special colour m	1000	Delivery time weeks special lab dip	2

CARE AND USAGE

Care code comments	iron on reverse side	Type of finish	Velvet
--------------------	----------------------	----------------	--------

Care codes

Care code for washing °C	Do not wash	Care code for bleaching	Do not bleach
--------------------------	-------------	-------------------------	---------------



Use codes

Curtains	Yes	Curtains and draperies	Yes
Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

ENVIRONMENTAL STANDARDS



FR STANDARDS

CAL 117 Complies	Yes	FMVSS 302 Pass	Yes
NFPA 260	Yes		

COLLECTION : CARRARA

ARTICLE : 8437

FABRIC SPECIFICATIONS

Composition	56% Viscose, 44% Cotton	Average yarn number	8.47
Construction	12x38.32	Woven	Yes
Useable width cm	1.43	Useable width inch	56.3
Full width cm	145	Full width inch	57.09
Weight g/m ²	582	Thickness mm	0.000
Colouring type	Piece dyed	Filament or staple	100% staple
Textured or non textured	100% not textured	Finish type	Velvet

Treatment

No treatment	Yes
--------------	-----

Type of print or dye

Reactive	Yes
----------	-----

Weaving type

Dobby	Yes
-------	-----

FABRIC TYPE

There are no technical details for this section.

COLLECTION : CARRARA

ARTICLE : 8437

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	4
Wyzenbeek double rubs	120,000	Pilling	4-5
Wyzenbeek wire screen double rubs	15,000	Wyzenbeek cotton duck double rubs	120,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	4-5
--------------------------	-----

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4
-------------------------	---

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	3-4
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strength warp N	51	Tearing strength weft N	48
-------------------------	----	-------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp N/5cm	540	Tensile strength weft N/5cm	930
-----------------------------	-----	-----------------------------	-----

Elongation - ISO 13934-1

Elongation warp %	7	Elongation weft %	11
-------------------	---	-------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp mm	3	Seam slippage weft mm	3
-----------------------	---	-----------------------	---

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing with steam	0.07
Dimensional change warp after ironing without steam	0.07	Dimensional change weft	0.08
Dimensional change weft after ironing with steam	0.20	Dimensional change weft after ironing without steam	0.00

COLLECTION : CARRARA

ARTICLE : 8437

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.93	Dimensional change warp after ironing	-2.73
Dimensional change weft	-0.10	Dimensional change weft after ironing	-0.07
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-3.10	Dimensional change warp after ironing	-3.93
Dimensional change weft	-0.67	Dimensional change weft after ironing	-0.80
Colour fastness ISO 105 C06	4		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.53	Dimensional change warp after ironing	0.20
Dimensional change weft	0.10	Dimensional change weft after ironing	0.20
Colour fastness ISO 105 D01	5		

CONSTRUCTION

Yarn 1

Weft Composition	100% Viscose	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/40S
Weft Threads per cm	21	Weft TPM	NA

Yarn 2

Weft Composition	100% Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	2/16S
Weft Threads per cm	17.32	Weft TPM	NA

Yarn 3

Warp Composition	100% Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/20S
Warp Threads per cm	11	Warp TPM	NA

See fabric on Twinbru

[COLLECTION : CARRARA](#)

[ARTICLE : 8437](#)

DOWNLOADS / CERTIFICATES

There are no technical details for this section.